J. Kej. Awam Jil. 7 Bil. 2 1994

# STRUCTURAL USE OF COATED FABRIC FOR LONG SPAN ROOFS - AN OVERVIEW

by

Mohamad Salleh Yassin Arizu Sulaiman Department of Structures & Materials Faculty of Civil Engineering Universiti Teknologi Malaysia

## ABSTRACT

One of the more visible developments in civil engineering in the past decade has been the utilization of coated fabrics as a major structural component for roofs of large spans. Fabric roofs can now be found throughout the world covering various types of structures such as sports stadia, ice rinks, swimming pools, leisure centres and other applications. Coated fabrics are now being used extensively in hot countries to create shades. The decision to use a fabric structure can be for one of three reasons: image, cost or some special property of the material, such as translucency or radio transparency. It is intended that this paper will provide an introductory overview of the technology of modern lightweight fabric structures by means of brief description and illustration of some technical aspects of such systems.

# INTRODUCTION

Membrane structures are ones in which the main load-carrying members transmit loads to the foundation or support system by tensile stresses with no compression or flexure allowed. They are referred to as load-adaptive due to the fact that the members re-shaping the geometry in order to accomodate any change in load rather than increasing the stress level.

Membrane structures can be divided into three subclasses[1]:

- i. Air-supported structures in which an enclosing membrane is supported by a small differential air pressure (Figure 1).
- ii. Prestressed membranes in which fabric is stretched over rigid frameworks and columns to form enclosures (Figure 2).
- iii. Hybrid systems in which fabrics panels are spanned between primary loadcarrying members such as prestressed cables and rigid members (Figure 3).

Membrane materials should have high tensile strength and should be flexible and light in weight. They should have good dimensional stability, be highly resistant to the propagation of minor accidental damage, and be easily and cheaply seamed or jointed in a reliable manner. Equally important, the materials should also be resistant to the environmental degredation and fire resistant.





Figure 1: Air supported structure



# COATED FABRICS

Coated fabrics consist of plain-weave fabrics processed with a coating material to produce a flexible, fibre-reinforced composite. The general properties that are important in a building application are listed in Figure 4 which shows the relative dependence of these properties upon the coating and the fabric. Table 1 gives several types of coated fabric materials along with their characteristics. The two materials that so far have found suvcess in building are PVC coated Polyester and PTFE coated glass.




Table 1 : Commonly Used Coated Fabric

.

\_

Materials         Cost(m <sup>-</sup> 2)         Tensile Strength         Elongation         Durability         Transiluencicy         Fire         Colour         Appliation           1. PVC canted Polyester         RM3 – RM2s         20 – 200         16 %         D         8 – 30 %         B         All         Widely used for air-house and fibric           1. PVC canted Polyester         RM3 – RM2s         20 – 200         16 %         D         8 – 30 %         B         All         Widely used for air-house and fibric           2. PVC Canted Polyester         RM3 – RM2s         20 – 200         20 %         D         8 – 30 %         B         All         Widely used forair-house and fibric           3. PVC Canted Nyalon         RM3 – RM2s         20 – 200         20 %         D         8 – 30 %         B         All         Widely used forair-house and fibric           3. PVC Canted Nopel         RM3 – RM2s         20 – 200         16 %         C         Opeque         B         All         Nuide opeint forair and area forair and area for area of a trabin and area of a tr	Source: Ref.[6]								
RM6 - RM28         20 - 200         16%         D         8 - 30%         B         All           RM6 - RM28         20 - 200         16%         D         8 - 30%         B         All           RM8 - RM28         20 - 200         20%         D         8 - 30%         B         All           ?         100 - 400         5%         C         Opaque         B         All           ?         100 - 400         5%         C         Opaque         B         All           ?         100 - 400         5%         C         Opaque         B         All           ?         100 - 400         5%         C         Opaque         B         All           ?         100 - 400         5%         C         Opaque         B         All           ?         100 - 400         5%         C         Opaque         B         All           ?         7         20         %         C         Opaque         B         All           ?         8         7         2         7         20%         B         All           ?         RM12         7         50%         B         All         2	Materials		Tensile Strength (kN/m)	Elongation	Durability	Translucency	Fire Resistance	Colour Ranges	Application
er       RM3 - RM28       20 - 200       20%       D       8 - 30%       B       AI         ?       100 - 400       5%       C       Opaque       B       AI         ?       100 - 400       5%       C       Opaque       B       AI         ?       100 - 400       5%       C       Opaque       B       AI         ?       100 - 400       5%       C       Opaque       B       AI         ?       100 - 400       5%       C       Opaque       B       AI         ?       100 - 400       5%       C       Opaque       B       AI         ?       RM32 - RM100       20 - 300       16%       C+       Opaque       B       AI         .       RM12 - RM32       50 - 200       16%       C       7 - 20%       B       AI         .       RM100       30 - 150       6%       A       5 - 15%       I       Ioony, some         .       A       2 - 25%       B       A       2 - 15%       B       5 - 0000       5 - 0000       5 - 000%       5 - 00%       B       5 - 00%       5 - 00%       5 - 00%       5 - 00%       5 - 00%       5 - 00%	1. PVC conted Polyester	RM8 – RM28	20 - 200	16 %	Q	8 - 30 %	8	R	Widely used for air - house and fabric
RM3 - RM28         20 - 200         20 %         D         8 - 30 %         B         All           ?         100 - 400         5 %         C         Opaque         B         All           ?         100 - 400         5 %         C         Opaque         B         All           ?         100 - 400         5 %         C         Opaque         B         All           ?         100 - 400         5 %         C         Opaque         B         All           ?         RM32 - RM100         20 - 300         16 %         C+         Opaque         B         All           RM12 - RM32         50 - 200         16 %         C         7 - 20 %         B         All           RM100 - RM18d         30 - 150         6 %         A         5 - 15 %         I         Iooy, some           .         A         20 - 50 %         B         A         20 - 50 %         B         50mc           .         A         20 - 50 %         B         B         50mc         50mc           .         A         20 - 50 %         B         B         50mc         50mc           .         A         20 - 50 %         B	Cloth with Acrylic Lacquer								structures. Can be coloured opague etc.
RM3 - RM28       20 - 200 $20\%$ D $8 - 30\%$ B       All         ?       100 - 400 $5\%$ C       Opaque       B       All         ?       100 - 400 $5\%$ C       Opaque       B       All         r       RM32 - RM100 $20 - 300$ $16\%$ C+       Opaque       B       All         RM12 - RM32 $50 - 300$ $16\%$ C+ $Opaque$ B       All         RM12 - RM32 $50 - 300$ $16\%$ C $7 - 20\%$ B       All         RM12 - RM18 $30 - 150$ $6\%$ A $5 - 15\%$ B       All         RM100 - RM18 $30 - 150$ $6\%$ A $5 - 15\%$ B       colours         . $A > 25 years$ $B > 20 - 25 years$ $A > 25 - 15 \%$ $B > 20 - 50 \psi$ $B > $									High translucent materials are less
RM3 - RM28 $20 - 200$ $20\%$ D $8 - 30\%$ B         All           ?         100 - 400         5%         C         Opaque         B         All           ?         100 - 400         5%         C         Opaque         B         All           rt         RM32 - RM100         20 - 300         16%         C+         Opaque         B         All           RM12 - RM32         50 - 300         16%         C+         Opaque         Not         All           RM12 - RM32         50 - 200         16%         C         7 - 20%         B         All           RM12 - RM13         30 - 150         6%         A         5 - 15%         I         Iooy, some           th         RM100 - RM18         30 - 150         6%         A         5 - 15%         B         colours           t         RM100         30 - 150         6%         B - A         20 - 50%         B         Some           RM100         30 - 150         6%         B - A         20 - 50%         B         colours           A $20 - 250$ erst         B - A         20 - 50%         B         colours         colours									durable. PVC laquer is now ava itable
RM3 - RM3 - RM28       20 - 200       20%       D       8 - 30%       B       All         ?       100 - 400       5%       C       Opaque       B       All         ?       100 - 400       5%       C       Opaque       B       All         RM32 - RM100       20 - 300       16%       C+       Opaque       B       All         RM12 - RM32       50 - 200       16%       C       7 - 20%       B       All         It       RM12 - RM32       30 - 150       6%       A       5 - 15%       1       Kony, some         it       RM100 - RM18d       30 - 150       6%       A       5 - 15%       B       All         it       RM100       30 - 150       6%       A       5 - 15%       B       colours         it       RM100       30 - 150       6%       A       20 - 50%       B       colours         it       RM100       30 - 150       6%       B - A       20 - 50%       B       colours         it       RM100       30 - 150       6%       B - A       20 - 50%       B       colours         it       A       20 - 50%       B       Some       colou				-					to give a more durable surface.
$^{7}$ 100 - 400       5%       C       Opeque       B       All         er       RM32 - RM100       20 - 300       16%       C+       Opeque       B       All         RM12 - RM32       50 - 300       16%       C+       Opeque       Not       All         RM12 - RM32       50 - 200       16%       C       7 - 20%       B       All         RM12 - RM32       30 - 150       6%       A       5 - 15%       1       Iooy, some         th       RM100 - RM18d       30 - 150       6%       A       5 - 15%       1       colours         th       RM100       30 - 150       6%       B - A       20 - 50%       B       Some         th       RM100       30 - 150       6%       B - A       20 - 50%       B       Some         th       RM100       30 - 150       6%       B - A       20 - 50%       B       Some         th       RM100       30 - 150       6%       B - A       20 - 50%       B       Some         th       A > 25 years       Fite resistance Grading : I       I virtually incline resistance Grading : I       I marketar         th       A > 25 years       B Fame resist<	2. PVC Conted Nyalon	RM8 - RM28	20 - 200	20%	D	8 - 30%	8	All	As above but less popular because of
?       100 - 400       5%       C       Opeque       B       All         er       RM32 - RM100       20 - 300       16%       C+       Opeque       B       All         RM12 - RM32       50 - 300       16%       C+       Opeque       B       All         RM12 - RM32       50 - 200       16%       C       7 - 20%       B       All         RM100       RM100       30 - 150       6%       A       5 - 15%       I       footy, some         ib       RM100       30 - 150       6%       A       5 - 15%       B       Some         it       RM100       30 - 150       6%       B - A       20 - 50%       B       Some         it       RM100       30 - 150       6%       B - A       20 - 50%       B       Some         it       RM100       30 - 150       6%       B - A       20 - 50%       B       Some         it       A       20 - 50%       B       B - A       20 - 50%       B       Some         it       A       20 - 50%       B       B - A       20 - 50%       B       Some         it       A       20 - 50%       B       Some </td <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td></td> <td>poor dimensional stability and creep.</td>									poor dimensional stability and creep.
er       RM32 - RM100 $20 - 300$ $16\%$ C+       Opaque       Not       All         RM12 - RM32 $50 - 300$ $16\%$ C+ $0$ paque       Not       All         RM12 - RM32 $50 - 200$ $16\%$ C $7 - 20\%$ B       All         Ith       RM10 - RM18d $30 - 150$ $6\%$ A $5 - 15\%$ I       Ivory, some         RM100 - RM18d $30 - 150$ $6\%$ A $5 - 15\%$ B       All         RM100 - RM18d $30 - 150$ $6\%$ B - A $20 - 50\%$ B       Some         RM100 - RM18d $30 - 150$ $6\%$ B - A $20 - 50\%$ B       Some         RM100 $30 - 150$ $6\%$ B - A $20 - 50\%$ B       Some         RM100 $30 - 150$ $6\%$ B - C $20 - 50\%$ B       Some         B $20 - 25$ years $RM100$ <t< td=""><td>3. PVC Conted Kevlar</td><td>\$</td><td>100 - 400</td><td>5%</td><td>U U</td><td>Opaque</td><td>B</td><td>Π</td><td>Would only be used where high</td></t<>	3. PVC Conted Kevlar	\$	100 - 400	5%	U U	Opaque	B	Π	Would only be used where high
cr       RM32 - RM100 $20 - 300$ $16\%$ C+       Opaque       Not       All         RM12 - RM32 $50 - 300$ $16\%$ C+ $Opaque$ Not       All         RM12 - RM32 $50 - 300$ $16\%$ C $7 - 20\%$ B       All         It       RM12 - RM32 $50 - 200$ $16\%$ C $7 - 20\%$ B       All         It       RM100 $80 - 150$ $6\%$ A $5 - 15\%$ I       hony, some         RM100 $30 - 150$ $6\%$ $B - A$ $20 - 50\%$ B       Some         RM100 $30 - 150$ $6\%$ $B - A$ $20 - 50\%$ B       Some         RM100 $30 - 150$ $6\%$ $B - A$ $20 - 50\%$ B       Some         RM100 $30 - 150$ $6\%$ $B - A$ $20 - 50\%$ B       Some         B $20 - 25$ years $R = resist       Colours B = 20 - 25 years       B = 20 - 25 years B = 20 - 25 years B = 20 - 25 years B = 20 - 25 years $									strength stiffeness required. Jointing
cr         RM32 - RM100         20 - 300         16 %         C+         Opeque         Not         All           RM12 - RM32         50 - 200         16 %         C         7 - 20 %         B         All           RM12 - RM32         50 - 200         16 %         C         7 - 20 %         B         All           th         RM12 - RM32         50 - 150         6 %         A         5 - 15 %         I         Ivory, some           th         RM100 - RM18(         30 - 150         6 %         A         5 - 15 %         I         iony, some           RM100         30 - 150         6 %         B - A         20 - 50 %         B         Some $t$ $A > 25 years         RM100         30 - 150         6 %         B - A         20 - 50 %         B         colours           t A > 25 years         File resistance Grading: I         Virtually incline resistance Grading:         B fame resist         colours           D         A > 20 - 20 years         B fame resist         Colours         Colours  $									problems. Must be opaque to protect
cr       RM:32 - RM:100 $20 - 300$ 16 %       C+       Opeque       Not       All         RM:12 - RM:32 $50 - 200$ $16 \%$ C $7 - 20 \%$ B       All         Ith       RM:12 - RM:32 $50 - 200$ $16 \%$ C $7 - 20 \%$ B       All         Ith       RM:00 - RM:84 $30 - 150$ $6 \%$ A $5 - 15 \%$ I       Ivory, some         RM:00 $30 - 150$ $6 \%$ A $5 - 15 \%$ B       Some         RM:00 $30 - 150$ $6 \%$ B - A $20 - 50 \%$ B       Some         RM:00 $30 - 150$ $6 \%$ B - A $20 - 50 \%$ B       Some         RM:00 $30 - 150$ $6 \%$ B - A $20 - 50 \%$ B       Some         RM:00 $30 - 150$ $6 \%$ B - A $20 - 50 \%$ B       Some         RM:00 $30 - 150$ $6 \%$ $B - 20 - 50 \%$ $B$ Some         R $20 - 25 \%$ $B - 25 \%$ $B$ $C - 25 \%$ $C - 25 \%$ $C - 25 \%$ R $20 - 50 \%$ $B - 25 \%$ <									Kevlar.
Image: RM12 - RM32     50 - 200     16 %     C     7 - 20 %     B     All       Image: RM100 - RM18d     30 - 150     6 %     A     5 - 15 %     1     Ivory, some       Image: RM100     30 - 150     6 %     A     5 - 15 %     1     Ivory, some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       Image: RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       I	4. Hypalon Coated Polyester	RM32 - RM100	20 - 300	16 %	с С	Opaque	Not	АШ	Used for radar domes. Hypalon
RM12 - RM32         50 - 200         16 %         C         7 - 20 %         B         All           th         RM100 - RM18(         30 - 150         6 %         A         5 - 15 %         I         Ivory, some           RM100         RM100         30 - 150         6 %         A         5 - 15 %         I         colours           RM100         30 - 150         6 %         B - A         20 - 50 %         B         some           RM100         30 - 150         6 %         B - A         20 - 50 %         B         colours           R000         30 - 150         6 %         B - A         20 - 50 %         B         colours           R000         30 - 150         6 %         B - A         20 - 50 %         B         colours           R000         30 - 150         6 %         B - A         20 - 50 %         B         colours           R 20 - 25 years         Fire resistance Grading :         I Virtually incFire resistance Grading :         B         colours           D - 15 years         Fire resistance Grading :         I A         B         A         b									degrades and powder on the surface
RM12 - RM32         50 - 200         16%         C         7 - 20%         B         All           th         RM100 - RM18(         30 - 150         6%         A         5 - 15%         I         Ivory, some           RM100         RM100         30 - 150         6%         A         5 - 15%         I         kory, some           RM100         30 - 150         6%         B - A         20 - 50%         B         some           i         A > 25 years         Fire resistance Grading :         I Virtually incline resistance Grading :         B         colours           B         20 - 25 years         Fire resistance Grading :         B         Flame resist         colours           D         10-52 years         Fire resistance Grading :         I         Nirtually incline resistance Grading :									can be repainted to extend life.
Ib     RM100 - RM18(     30 - 150     6 %     A     5 - 15 %     I     Ivory, some       RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       RM100     30 - 150     6 %     B - A     20 - 50 %     B     Some       C     15 - 20 years     Fire resistance Grading :     I Virtually incFire resistance Grading :     B     Colours       D     10 - 15 wears     B     A     20 - 50 wears     B     Colours	5. PVC Conted Polyester	RM12 - RM32	50 - 200	16%	с С	7 - 20%	8	ΝĪ	Used occsionally in USA. Laminate
Ib         RM100 - RM18(         30 - 150         6 %         A         5 - 15 %         I         Ivory, some           RM100         30 - 150         6 %         B - A         20 - 50 %         B         Some           RM100         30 - 150         6 %         B - A         20 - 50 %         B         Some           A         >25 years         Fire resistance Grading : I         Virtually incFire resistance Grading :         I         virtually incFire resistance Grading :           B         20 - 25 years         Fire resistance Crading :         I         Virtually incFire resistance Grading :           D         10 - 15 wears         B         A         A         A         A	with Tedlar								provides a stay clean surface. Welded
th         RM100 - RM18d         30 - 150         6%         A         5 - 15%         I         Ivory, some           RM100         30 - 150         6%         B - A         20 - 50%         B         Some           A         >25 years         Fire resistance Grading: I         Virtually mcFire resistance Grading:         B         colours           B         20 - 25 years         Fire resistance Grading:         B         Flame resistance Grading:           D         10 - 15 wears         B         Flame resistance Grading:         B									jointa have low strength.
RM100     30 - 150     6 %     B - A     20 - 50 %     B     colours       :     A     > 25 years     Fire resistance Grading: I Virtually mcFire resistance Grading: B     20 - 50 %     B     colours       :     A     > 25 years     Fire resistance Grading: B     I Virtually mcFire resistance Grading: D     0.15 were	5. PTFE Costed Glass Cloth	RM100 - RM180	30 - 150	6%	۷	5 - 15 %	I	Ivory, some	Has been widely used for "permanent'
RM100         30 - 150         6%         B - A         20 - 50%         B         Some           :         A         > 25 years         Fire resistance Grading : I         Virtually incline resistance Grading : E         colours           B         20 - 25 years         Fire resistance Grading : I         Virtually incline resistance Grading : C         1 Virtually incline resistance Grading : D         0.015 week								colours	fabric structures.
A     > 25 years     Fire resistance Grading:     colours       B     20 - 25 years     B     Fine resistance Grading:       B     20 - 25 years     B     Flame resistance Grading:       D     10 - 15 years     B     Flame resistance Grading:	6. Silicon Conted Glass	RM100	30 - 150	6%	B – A	20 - 50 %	æ	Some	New material.
: A > 25 years Fire resistance Grading : I Virtually incFire resistance Grading : B 20 - 25 years B Flame resist C 15 - 20 years B flame retari D 10 - 15 years								colours	
20 - 25 years 15 - 20 years 10 - 15 weeks	Notes : Durability Grading :	A > 25 years		Fire resistance	: Grading :	I Virtually incl	Fire resistance	: Grading :	I Virtually incombustible
15 - 20 years 10 - 15 years						<b>B</b> Flame resist			B Flame resistant with the addition of
10 – 15						flame retard			flame retardant salts.

# STRUCTURAL BEHAVIOUR

A coated woven fabric is considered anisotropic because of the behaviour caused by its interstructure as well as the coating condition of the fabric (Figure 5). The peculiarities of fabric in respond to applied loads may attribute to the deformation of one or more mechanisms dominating in certain ranges of loading.




Figure 5: Schema of coated fabric


Figure 6 shows a typical, idealized, general stress-strain response of coated fabric. It can be seen that the shape of the stress-strain characterictics is governed by the mutual interaction between the warp and weft fibres.


### DESIGN ASPECT

The design of prestressed membranes structures using coated fabrics will usually commence from an architectural sketch in order to outline the space spanning requirements: Unlike in the case of conventional structures, at a stage much earlier the engineer will have to work hand to hand with the architect in the development of the design concept. The principle reason for this is that tensile membranes, in practice, are shear-free prestressed mechanisms of which the form is governed by the surface stress ratios in the main weave direction of the fabric. The process of designing a fabric roof involves the achievement of a number of goals[3].

- i. Defining the surface geometry (Form finding).
- ii. Analysing the structure's response to load (Load Response).

iii. Dimensioning the parts (Fabrication patterning).






## Form Finding

At the conceptual design stage, simple physical modelling for instance using stockinette material (Figure 7), is effective since it allows a direct communication of design ideas between architect and engineer; And, through the examination of surface curvatures, gives useful guidance on preferred patterning and stress ratios. Even at this stage, however, it is useful to employ, in parallel, a computer simulation of the structural form (Figure 8).

. ...



İ

Starting from the basic boundary co-ordinates, the computer calculates where prescribed forces should lie in space for them to be in equilibrium. One such method called "Dynamic Relaxation"[3] is based upon the fact that to get from one state of equilibrium to another, a structure must move. By writing the equation of motion for the structure and applying damping to make the structure come to rest, one is following exactly the procedure that happen in nature. The method allows one to choose the loading conditions for defining the basic form which optimises the structural behaviour. Computerised methods avoid the serious measurement errors which can occur with physical methods. However, physical models still have the advantage of giving the designer physical understanding.

#### Load Response

There are two aspects to be studied. The first is to make a design which intrinsically can be prestressed. The second aspect concerns what forces are set up within the membrane during the introduction of prestressing forces and applied load.


Calculation has to be made which establishes the strength characteristic required for the membrane material and its joints. Together with that, studies to find the critical load combinations during erection and service life have to be made. Wind intensities can be established via Codes of Practice and wind tunnel testing.

A non linear method of analysis, such as Dynamic Relaxation can be used to allow for the large changes in geometry that occur under each pattern of applied loads.

## **Fabrication Patterning**

A feature common to all fabric membranes is that the surfaces are manufactured using patterns, as dressmaking, such that when the parts are jointed together they produce a doubly curved surface.

Traditionally this has been done by making accurate models of the surface, laying elements on these model and expanding the resulting patterns by a scale factor (Figure 9).



# ADVANTAGES OF COATED FABRICS STRUCTURES

Membranes or fabric structures are well suited to broadly distribute dead loads and live loads such as wind and drift forces due to waves. It should not be surprising that lightweight fabric structures will become a popular choice of roofing system for the next decade.

Some advantages of coated fabric usage as structural components are[1,4]:

- i. It can provide vast, clear span space-without large supporting members.
- ii. It is lightweight and collapsible and therefore easy to transport and erect.
- iii. It is entirely pre-fabricated off-site, thereby making erection simple, fast and economical.
- iv. It creates outdoor space by protecting against U.V.rays, heat, glare, rain and wind.
- v. Natural light through translucent shade sails is soft and cool by day, and dramatic lighting effect can be achieved at night to create a landmark structure.
- vi. Design freedom with state-of-the-art materials and process technologies recast an otherwise boring commercial facility into exciting, distinctive community space.

#### APPLICATIONS

Fabric roofs can now be found throughout the world covering various types of building structures.

The world largest shade structure-the Haj Terminal at Jeddah International Airport covers  $500,000m^2$  and consists of  $45m \times 45m$  mechanically tensioned prestressed membrane surfaces made from PTFE coated glass and reinforced with radial cables. The material's high surface reflection and structural forr help in reducing air temperature under the roof (Figure 11).

A dramatic 50m by 50m fabric roof over two sunken tennis court at Royal Pin Resort, Carrara, on the Gold Coast, Australia (Figure 12).

The wave-form shade structures for EXPO 88, Brisbane consist of sev interconnected segmental tents with polyester fabric membrane of 35 000 total area stressed between ridge and valley radial cables (Figure 13).





Figure 12: Tennis court at Royal Pines Resort.



Large areas of sunshading have also been built in other parts of the world using either PVC coated polyester or PTFE coated glass fabric.

## CONCLUSION

Even though these types of structures have been erected in many parts of the world, the developments in Malaysia are still new. Review on some technical aspects presented here will be beneficial to the development of this potential structural material.

#### REFERENCES

- 1. Leonard, J. W.: Tension Structures, McGraw-Hill, New York, 1988
- Schock, H. J.: 'On The Structural Behaviour and Material Characteristics of PTFE-Coated Glass-Fibre Fabric', Journal of Coated Fabrics, Vol.20 April 1991
- Barnes, M. R., Wakefield, D. S.: 'Form-finding, analysis and patterning of surfaced-stressed structures', 1st Oleg Kerensky Memorial Conference, London 1988
- 4. Salvadori, M., Heller, R.: Structure in Architecture, Prentice Hall, New Jersey, 1975
- 5. Forster, B.: 'The Engineered Use of Coated Fabrics in Long Span Roofs', Journal of Coated Fabrics, Vol.15 July 1985
- Liddell, W. I.: Current Development in materials for fabric structures, Proceedings of the 1st. International Conference on Lightweight Structures in Architecture, Australia, 1986
- 7. Barnes, M. R.: 'Computer Aided Design of the shaded membrane roofs for EXPO 88', Structural Engineering Review, 1988